

PROFORM® BRAND PERFECT SPRAY® EM

MANUFACTURER

National Gypsum Company
2001 Rexford Road
Charlotte, NC 28211
(704) 365-7300

Technical Information:
1-800-NATIONAL
(1-800-628-4662)

Fax: 1-800-FAX NGC1
(1-800-329-6421)

Internet Home Page:
www.nationalgypsum.com
09250/NGC Buyline: 1100

DESCRIPTION

A nonaggregated texture, ProForm® BRAND Perfect Spray® EM is used to create a wide range of wall surfaces.

BASIC USES

By adjusting mixture consistency and/or varying the atomizing pressure, ProForm Perfect Spray EM creates an almost endless variety of textures, the most typical of which are Spray Spatter, Spatter Knock-Down and Orange Peel. Surfaces can be finished with a coat of paint. Perfect Spray EM can be used for both walls and ceilings.

AGGREGATE SIZES

None

PACKAGING

Bag size: 50 lbs (23 kg)

COMPOSITION & MATERIALS

Contains no asbestos.

Component	CAS No.
Limestone	1317-65-3
Quartz	14808-60-7

May contain one or more of the following:

Talc (nonasbestos)	14807-96-6
Titanium Dioxide	13463-67-7
Mica	12001-26-2
Clay	12174-11-7
	8031-18-3
	63800-37-3
	1332-58-7
	1335-30-4

Diatomaceous Earth (Uncalcined)	61790-53-2
Starch	53124-00-8
	113894-92-1
	9005-27-0
Perlite	93763-70-3
Vermiculite	1318-00-9
Polystyrene	9003-53-6

Caution: *CONTAINS MICA AND TITANIUM DIOXIDE. Do not take internally. KEEP OUT OF REACH OF CHILDREN.*

TECHNICAL DATA

Water-to-bag mix: 4-5 gal. (15-19 L)

Coverage per bag: Normal coverage of ProForm Perfect Spray EM is 10-30 sq. ft./lb. (2.0-6.1 M²/kg) depending on the type of equipment used and the type of texture desired.

SURFACE BURNING CHARACTERISTICS

ASTM E 84	
Flame Spread	15
Smoke Developed	0

INSTALLATION

APPLICABLE STANDARDS AND REFERENCES

ASTM C 840
Gypsum Association GA-216
Gypsum Association GA-214
National Gypsum Co. Gypsum Construction Guide

RECOMMENDATIONS

In cold weather (outside temperatures below 50°F [10°C]), temperatures within the building should be maintained at a minimum 50°F (10°C), both day and night, before and during

spray operations and until sprayed surfaces have fully dried. Adequate ventilation should be provided to eliminate excess moisture.

Mix dry texture material in accordance with instructions printed on the bag.

Gypsum wallboard: Surfaces, including joint-treated areas, must be smooth, clean and dry. First apply a coat of good-quality, sealing latex primer. Mask appropriate areas before spraying, and promptly remove overspray from unprotected surfaces afterward. Follow the instructions of the spray equipment manufacturer for adjusting controls and cleaning. If a second coat is desired, allow the first coat to dry completely. Surface then must be painted after texture is dry.

Concrete: Allow concrete to cure for at least 28 days. Clip protruding wire ends and spot with rust-inhibitive primer. Remove all form oil, grease and dirt, or any loose or water-soluble material. Grind down any form ridges and level any remaining unevenness with ProForm Sta-Smooth Joint Compound. Apply a coat of alkali-resistant, sealing latex primer over the entire surface to be textured.

Use of a respirator and eye protection is recommended during spray application.

Apply Perfect Spray EM to prepared surface with appropriate equipment, following equipment manufacturer's instructions.

Caution: Avoid creating dust. When mixing, ventilate area, wear eye protection and a NIOSH- or MSHA-approved respirator for dust. Keep out of reach of children.

Note: Complete, easy-to-follow application instructions are printed on all bags of ProForm Textures. Close adherence to instructions for surface preparation and priming will avoid the problems of color variation, bleeding or sagging and will permit the texture to achieve its full potential.

DECORATION

Perfect Spray EM is not considered a finished surface. However, it needs no further preparation in order to be painted with a latex paint.

National Gypsum

Excellence Across The Board

Job Name _____

Contractor _____ Date _____

Submittal Approvals: (Stamps or Signatures)