

# PROFORM® BRAND PERFECT SPRAY®

## MANUFACTURER

National Gypsum Company  
2001 Rexford Road  
Charlotte, NC 28211  
(704) 365-7300

Technical Information:  
1-800-NATIONAL  
(1-800-628-4662)

Fax: 1-800-FAX NGC1  
(1-800-329-6421)

Internet Home Page:  
www.nationalgypsum.com  
09250/NGC Buyline: 1100

## DESCRIPTION

ProForm® BRAND Perfect Spray® is a decorative texture with a shredded polystyrene aggregate, designed for spray application.

### BASIC USES

Perfect Spray's white, bold texture effectively hides minor surface defects and irregularities. Perfect Spray readily mixes with water to deliver the consistency and application control desired.

### AGGREGATE SIZES

Coarse  
Medium  
Fine

### PACKAGING

32 lb. bag (15 kg)  
40 lb. bag (18 kg)  
50 lb. bag (23 kg)

### COMPOSITION & MATERIALS

Contains no asbestos.

Component	CAS No.
Limestone	1317-65-3
Quartz	14808-60-7

May contain one or more of the following:

Talc (nonasbestos)	14807-96-6
Titanium Dioxide	13463-67-7
Clay	12174-11-7
	8031-18-3
	63800-37-3
	1332-58-7
	1335-30-4
Mica	12001-26-2
Diatomaceous Earth (Uncalcined)	61790-53-2
Starch	53124-00-8
	113894-92-1
	9005-27-0
Perlite	93763-70-3
Vermiculite	1318-00-9
Polystyrene	9003-53-6

Caution: CONTAINS MICA AND TITANIUM DIOXIDE. Do not take internally. KEEP OUT OF REACH OF CHILDREN.

## INSTALLATION

### APPLICABLE STANDARDS AND REFERENCES

ASTM C 840  
Gypsum Association GA-216  
Gypsum Association GA-214  
*National Gypsum Co. Gypsum Construction Guide*

### RECOMMENDATIONS

Installation of ProForm Perfect Spray should be consistent

## TECHNICAL DATA

Aggregate: shredded polystyrene

### SURFACE BURNING CHARACTERISTICS

ASTM E 84	
Flame Spread	15
Smoke Developed	0

### COVERAGE

Bag Size	40 lbs. (18 kg)	32 lbs. (14 kg) (West Coast only)
Mixing Water	3 - 4 gal. (11-15 L)	4 - 5 gal. (15-19 L)
Bag Coverage	300 - 400 sq.ft. (27-36 M <sup>2</sup> )	250-300 sq.ft. (22-27 M <sup>2</sup> )

Note: Coverage of Perfect Spray will vary with the type of equipment used and the type of finish desired. Good hide and appearance can be accomplished if it is applied at a rate not to exceed 8 to 10 square feet (0.7 to 0.9 M<sup>2</sup>) per pound (0.42 kg). At coverage rates less than 8 sq. ft. per pound, two coats are recommended. Allow the first coat to dry thoroughly before applying the second.

with methods described in the noted standards and references and as indicated below.

In cold weather (outside temperatures below 50°F [10°C]), temperatures within the building should be maintained at a minimum 50°F (10°C), both day and night, before and during spray operations and until sprayed surfaces have fully dried.

Adequate ventilation should be provided to eliminate excess moisture.

*Gypsum wallboard:* Surfaces, including joint-treated areas,

must be smooth, clean and dry. When texturing is the finished surface, first apply a coat of good-quality, white sealing latex primer. Mask appropriate areas before spraying, and promptly remove overspray from unprotected surfaces afterward. Follow the instructions of the spray equipment manufacturer for adjusting controls and cleaning. If a second coat is desired, allow the first coat to dry completely.

*Concrete:* Allow concrete to cure for at least 28 days. Clip protruding wire ends and spot with rust-inhibitive primer. Remove all form oil, grease and dirt, or any loose or water-soluble material. Grind down any form ridges and level any remaining unevenness with ProForm Sta-Smooth Joint Compound. Apply a coat of alkali-resistant, sealing latex primer over the entire surface to be textured.

### SPRAY EQUIPMENT

*Low pressure:* Hopper-type hand guns should have nozzle openings of 1/4" to 3/8" and operating pressures of 20 to 30 psi.

(Continued next page)

Job Name \_\_\_\_\_

Contractor \_\_\_\_\_ Date \_\_\_\_\_

Submittal Approvals: (Stamps or Signatures)

*High pressure:* Pole guns should have nozzle openings of 1/4" to 3/8", feed pressure of 40 to 60 psi, and air pressure of 80 to 120 psi at the tank. (As a general rule, air pressure in the tank should be twice that of the material pressure.)

*Caution:* Avoid creating dust. When mixing, ventilate area, wear eye protection and a NIOSH- or MSHA-approved respirator for dust. Keep out of reach of children.

*Note:* Complete, easy-to-follow application instructions are printed on all bags of ProForm Textures. Close adherence to instructions for surface preparation and priming will avoid the problems of color variation, bleeding or sagging and will permit the texture to achieve its full potential.

**National**   
**Gypsum**®

**Excellence Across The Board** 