

GOLD BOND® BRAND FOIL BACK GYPSUM BOARD

MANUFACTURER

National Gypsum Company
2001 Rexford Road
Charlotte, NC 28211
(704) 365-7300

Technical Information:
1-800-NATIONAL
(1-800-628-4662)

Fax: 1-800-FAX NGC1
(1-800-329-6421)

Internet Home Page:
nationalgypsum.com
nationalgypsum.com/espanol

09 29 00/NGC BuyLine: 1100

DESCRIPTION

Gold Bond® BRAND Foil Back Gypsum Board Panels consist of a fire-resistive gypsum core encased in heavy natural-finish paper on the face side and strong liner paper on the backside to which aluminum foil is laminated. The ends are square-cut and finished smooth.

BASIC USES

Foil Back Gypsum Board can be used for exterior walls and ceilings in new construction and remodeling. The aluminum foil, laminated to the back surface, is a vapor retarder to keep interior moisture within the building at a suitable comfort level. For use with furred masonry, wood or steel framing, Foil Back Gypsum Board is effective for single-layer applications and as a base layer in double-layer applications where a vapor retarder of 1 perm or less is required.

ADVANTAGES

- In tests conducted according to ASTM Test Procedure E 96 (desiccant method), Foil Back Gypsum Board showed a performance of less than 0.01 perm compared to approximately 34 perm for 1/2" regular gypsum board and approximately 28 perm for 1/2" gypsum board with two coats of flat latex paint.
- In-place cost of Foil Back Gypsum Board installation is lower per thousand sq. ft. than a similar installation for

regular gypsum board and polyethylene-film retarder installed separately.

- Easy-to-handle Foil Back Gypsum Board is adaptable to virtually all exterior wall and ceiling construction: wood frame, steel frame, furred masonry.

LIMITATIONS

- Not recommended for use where exposure to moisture and high outside temperature is extreme and continuous. Under these conditions, a qualified mechanical engineer should determine location of the vapor retarder.
- Not recommended to be used over kraft-faced insulation or other vapor retarders.
- Not to be exposed to temperatures exceeding 125°F (52°C) for extended periods of time.
- Foil Back Gypsum Board must be stored off the ground and under cover. Sufficient risers must be used to assure support for the entire length of the gypsum board to prevent sagging.

- Not to be used as a base for ceramic or other tile or as a base layer for prefinished vinyl wall panels in double-layer assemblies.
- Not to be used as a base for adhesively applied vinyl or other highly water-vapor-resistant wall coverings.
- Foil Back Gypsum Board is not recommended for use in hot, humid climates such as the Southern Atlantic and Gulf Coast areas.
- The foil surface of Foil Back Gypsum Board is not recommended for lamination to any surface.
- To prevent objectionable sag in gypsum paneled ceilings, the weight of overlaid unsupported insulation should not exceed the following recommendations:

PSF (Pounds per Sq. Ft.)	Type	Frame Spacing
1.3 (6.3 kg/M ²)	1/2" Regular	24" o.c.
2.2 (10.7 kg/M ²)	1/2" Regular	16" o.c.
2.2 (10.7 kg/M ²)	5/8" Fire-Shield	24" o.c.

Panels 3/8" thick must not be overlaid with unsupported insulation. If required, a vapor retarder can be installed in exterior ceilings, and plenum or attic spaces should be properly vented.

COMPOSITION & MATERIALS

Foil Back Gypsum Board is a manufactured panel with a gypsum core encased in paper. Aluminum foil is laminated to the back side.

ACCESSORIES

- Fasteners: drywall screws or nails
- ProForm Joint Tape
- ProForm Ready Mix or ProForm Quick Set/Quick Set Lite Setting Compound
- Cornerbead, trims, casing beads
- Furring channels
- E-Z Strip control joints or .093 zinc control joints

(Continued next page)

Job Name _____

Contractor _____ Date _____

Submittal Approvals: (Stamps or Signatures)

TECHNICAL DATA

PHYSICAL PROPERTIES

Thickness, nominal	1/2" Regular (12.7 mm)
Thickness, nominal	5/8" Type X (15.9 mm)
Width, nominal	4' (1219 mm)
Length, standard	6' through 16' (1829-4877 mm)
Weight, lbs./sq. ft., nominal	1/2" Regular - 1.6
Weight, lbs./sq. ft., nominal	5/8" Type X - 2.2
Edges	Tapered, Square or Sta-Smooth
Surface Burning Characteristics (per ASTM E 84)	Flame Spread: 15 Smoke Developed: 0

APPLICABLE STANDARDS AND REFERENCES

ASTM C 1396

ASTM C 840

Gypsum Association GA-214

Gypsum Association GA-216

Gypsum Association GA-801

National Gypsum Company, *Gypsum Construction Guide*

FIRE RESISTANCE RATINGS

Foil Back Gypsum Board has not been used in fire resistance tests. Fire resistance ratings represent the results of tests on assemblies made up of specific materials in a specific configuration. When selecting construction designs to meet certain fire resistance requirements, caution must be used to ensure that each component of the assembly is the one specified in the test. Further, precaution should be taken that assembly procedures are in accordance with those of the tested assembly. (For copies of specific tests, call 1-800-NATIONAL.)

to equalize the porosities between surface paper and joint compound.

The selection of a paint to give the specified or desired finished characteristics is the responsibility of the architect or contractor.

Foil Back Gypsum Board that is to have a wallcovering applied to it should be prepared and primed as described for painting. See LIMITATIONS note on certain wallcoverings.

Gypsum Association GA-214, *Recommended Specification for Levels of Gypsum Board Finish*, should be referred to in order to determine the level of finishing needed to assure a surface properly prepared to accept the desired decoration.

INSTALLATION

RECOMMENDATIONS

Installation of Foil Back Gypsum Board should be consistent with methods described in the noted standards and references.

DECORATION

For best painting results, all interior surfaces, including joint compound, should be clean, dust-free and not glossy. To improve fastener and joint concealment, a coat of a quality drywall primer is recommended

National 
Gypsum®